



Object in rapport opgenomen: V 2466 (KN&V)
 Kunstenaar / Maker: Ettore Sottsass, Innsbruck 1917 - Milaan 2007
 Object Naam / Titel: Vistosi schaal : Orsete
 Periode: 20e eeuw
 Datum: 1972
 Materiaal en techniek: glas appliceren
 Afmetingenlabel: 9,8 x 33,6 cm
 Creditline intern: Schenking H.A. Dommissie, 2006

Aanleiding conditierapport

Project

Rapportnummer: 2023.498 Onderzoeker: Mandy Slager Begindatum: 23-03-2023 Master Rapport

Algehele toestand: matig Behandeling Prioriteit: behoeft onderzoek

Conserveringsrapport gerelateerde Personen / Instellingen (1)

Rol	Naam tonen als
Rapport opgesteld door	Mandy Slager

▼ CONDITION CHECK

a. material information

a.1 material(s)	
a.2 manufacturing detail(s)	

b. condition general

b.1 scratch(es) or abrasion	<input type="checkbox"/>	
b.2 crack(s)	<input type="checkbox"/>	
b.3 fracture(s)	<input type="checkbox"/>	
b.4 lacuna(e)	<input type="checkbox"/>	
b.5 dust, dirt or stain(s)	<input checked="" type="checkbox"/>	* dust and fibres on the surface of the glass (mostly upper surface)
b.6 other	<input type="checkbox"/>	

▼ SYMPTOMS OF ATMOSPHERIC DETERIORATION

c. potential symptoms

c.1 cloudy appearance (flecks or haze)	<input checked="" type="checkbox"/>	* with light in specific direction from underneath flecks become apparent: patterned but overall
c.2 slippery surface	<input checked="" type="checkbox"/>	* top surface: slippery more towards the rim and on the rim, but not so much in centre * on unc
c.3 deposit - 1. fingerprint(s)	<input type="checkbox"/>	
c.3 deposit - 2. dust	<input checked="" type="checkbox"/>	* dust and fibres on glass surface
c.4 possible colour alteration	<input type="checkbox"/>	
c.5 other	<input type="checkbox"/>	

d. stages of atmospheric deterioration

d.1 deposit - 1. droplets	<input type="checkbox"/>	
d.1 deposit - 2. crystals	<input type="checkbox"/>	
d.2 crizzling - 1. incipient	<input type="checkbox"/>	
d.2 crizzling - 2. full-blown	<input type="checkbox"/>	
d.2 crizzling - 3. advanced	<input type="checkbox"/>	
d.2 crizzling - 4. fragmented	<input type="checkbox"/>	

▼ EXAMINATION AND ANALYSIS

e. examination and analysis




e.1 visual	<input checked="" type="checkbox"/>	
e.2 microscopy	<input checked="" type="checkbox"/>	
e.3 ultraviolet light	<input type="checkbox"/>	
e.4 ion chromatography	<input checked="" type="checkbox"/>	* Unstable: samples and IC analysis were carried out by G. Verhaar and others in 2020. See result
e.5 x-ray fluorescence	<input checked="" type="checkbox"/>	* Analysis was carried out on 18-12-2022 on RCE Erfgoed Labdag
e.6 fractography	<input type="checkbox"/>	
e.7 other	<input type="checkbox"/>	

▼ IMAGING

f. imaging	
f.1 photography	<input checked="" type="checkbox"/>
f.2 microscopy	<input checked="" type="checkbox"/>
f.3 reflectance transformation	<input type="checkbox"/>
f.4 annotated mapping	<input checked="" type="checkbox"/>
f.5 other	<input type="checkbox"/>

Verwante Media kruisverwijzingen - Conserveringsrapporten

Verwante Media kruisverwijzingen - Conserveringsrapporten
🖼️ + ✖️ 🔍 📄

								
V2466KNV_Annotatie_1 annotatie	V2466KNV_Annotatie annotatie	V2466KNV_CF_13102022 conditiefoto	V2466KNV_CF_13102022 conditiefoto	V2466KNV_CF_13102022 conditiefoto	V2466KNV_CF_13102022 conditiefoto	V2466KNV_CF_13102022 conditiefoto	V2466KNV_CF_13102022 conditiefoto	V2466KNV_OR_01082023 Onderzoek
							 	 

▼ TREATMENT

g. previous treatment		
g.1 cleaning	<input checked="" type="checkbox"/>	* 2013: with demineralized water and ethanol in ratio 4:1.
g.2 consolidation or adhesion	<input type="checkbox"/>	
g.3 filling	<input type="checkbox"/>	
g.4 other	<input type="checkbox"/>	

h. suggestions (preventive) treatment

h.1 handling	<input checked="" type="checkbox"/>	* object might be or become slippery: careful with nitrile gloves when handling the object
h.2 support	<input type="checkbox"/>	
h.3 packing/transport	<input type="checkbox"/>	
h.4 numbering	<input type="checkbox"/>	
h.5 climate	<input checked="" type="checkbox"/>	* keep up to date with state of the art knowledge on climate control of unstable glass
h.6 monitoring	<input checked="" type="checkbox"/>	* monitoring condition of objects part of the reference collection at regular intervals is important
h.7 cleaning	<input type="checkbox"/>	
h.8 other treatment	<input type="checkbox"/>	
h.9 mounting/display	<input type="checkbox"/>	
h.10 further research	<input checked="" type="checkbox"/>	* comparison analytical results IC and XRF with other objects (own collection and for example co

▼ COMMENTS

Comments - general B I U      

▼ PROJECT

project + ✖️

P.1049 4. ACTIEF Collectie en Onderzoek 